

Beyond Calacatta

Porcelain tiles



Scan to learn more

Size $11\frac{3}{4}'' \times 23\frac{5}{8}''$ Thickness ± 9 mm Finish Matte, Polished
 $23\frac{5}{8}'' \times 47\frac{1}{4}''$

V2 SLIGHT VARIATION



Field tiles	Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	Edge
	12" x 24"	$11\frac{3}{4}'' \times 23\frac{5}{8}''$	9 mm	Matte	Rectified
	3D Etch	$11\frac{3}{4}'' \times 23\frac{5}{8}''$	9 mm	Matte	Rectified
	24" x 48"	$23\frac{5}{8}'' \times 47\frac{1}{4}''$	9 mm	Matte, Polished	Rectified
Mosaics and coordinating trims	Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	
	Mosaic 2" x 2"	$11\frac{3}{4}'' \times 11\frac{3}{4}''$	9 mm	Matte	Please refer to caliber chart for working size. Close joints are not recommended.
	Picket Mosaic	$12\frac{2}{7}'' \times 11\frac{5}{7}''$	9 mm	Matte	
	Bullnose 3" x 24"	$2\frac{7}{8}'' \times 23\frac{5}{8}''$	9 mm	Matte, Polished	
	Cove Base 6" x 12"	$5\frac{7}{8}'' \times 11\frac{3}{4}''$	8.5 mm	Matte	

Property	Test Method	Requirements			
		Calibrated	Rectified		
Regularity characteristics	Nominal Size		$\pm 3.00\%$	-3.00% ÷ +2.00%	Compliant
	Caliber Range	ASTM C499	$\pm 0.50\%$ or ± 0.08 in (± 2.0 mm) (*)	$\pm 0.25\%$ or ± 0.03 in (± 0.8 mm) (*)	Compliant
	Thickness ⁽¹⁾		Range: 0.04 in (1.02 mm)		Compliant
	Wedging	ASTM C502	$\pm 0.50\%$ or ± 0.08 in (± 2.0 mm) (*)	$\pm 0.25\%$ or ± 0.03 in (± 0.8 mm) (*)	Compliant
	Warpage Edge	ASTM C485	$\pm 0.75\%$ or ± 0.09 in (± 2.3 mm) (*)	$\pm 0.40\%$	Compliant
Warpage Diagonal	$\pm 0.50\%$ or ± 0.08 in (± 2.0 mm) (*)		$\pm 0.40\%$ or ± 0.07 in (± 1.8 mm) (*)	Compliant	
Structural characteristics	Water Absorption	ASTM C373	$\leq 0.5\%$		$\leq 0.5\%$
Bulk mechanical characteristics	Breaking Strength	ASTM C648	Average ≥ 250 lbf. (1.11 kN) Individual ≥ 225 lbf. (1.00 kN)		≥ 350 lbf. avg
Physical properties	Bond Strength	ASTM C482	≥ 50 psi. (0.34 Mpa)		≥ 100 psi.
Thermal and hygrometric characteristics	Resistance to Freeze/Thaw Cycling	ASTM C1026	As Reported		Resistant
	Thermal Shock Resistance	ASTM C484	As Reported		Resistant
Chemical characteristics	Chemical Resistance	ASTM C650	As Reported		Unaffected
	Stain Resistance	ASTM C1378	As Reported		Unaffected
Safety characteristics	Dynamic Coefficient of Friction (DCOF)	ANSI A326.3	As Reported ⁽²⁾	Matte	Polished
				≥ 0.42 Wet Interior Wwet (IW) ⁽²⁾	≥ 0.42 Dry Interior Dry (ID) ⁽²⁾

(*) Whichever is less
 (1) May not apply to textured surfaces or tiles with uneven back patterns.
 (2) DCOF ≥ 0.42 Wet may not be a requirement for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations.
 For updated manufacturer classification according to ANSI A326.3, Section 4 - "Product Use Categories", please refer to our website.

For more details please see the catalogue or visit atlasconcordeusa.com
 The Health Product Declaration® logo is a registered trademark of HPD Collaborative.

